

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 969 019 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.01.2000 Bulletin 2000/01

(51) Int. Cl.⁷: **C08F 4/62, C08F 210/16**

(21) Application number: 98112233.6

(22) Date of filing: 02.07.1998

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(71) Applicant: FINA RESEARCH S.A.
B-7181 Seneffe (Feluy) (BE)

(72) Inventors:
• Razavi, Abbas
7000 Mons (BE)
• Peters, Liliane
1495 Marbais (BE)

(54) Polyolefin production

(57) Use of a metallocene catalyst component of general formula $R''(CpR_m)(Cp'R'_n)MQ_2$ in the production of linear low density polyolefin, wherein Cp is a cyclopentadienyl moiety, Cp' is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge imparting stereorigidity to the component; each R is independently hydrogen or hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq m \leq 4$; each R' is independently hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq n \leq 8$; M is a Group IVB transition metal or vanadium; and each Q is hydrocarbyl having 1 to 20 carbon atoms or halogen; the metallocene having a centroid-M-centroid angle in the range 105° to 125°.

EP 0 969 019 A1

Description

[0001] The present invention relates to a process for the preparation of polyolefins, especially polyethylenes, the use of metallocene compounds as catalyst components in the production of such polyolefin and the polyolefins obtainable thereby.

[0002] Low density polyethylene (LDPE) offers excellent optical properties and can be processed at relatively low temperatures and pressures while maintaining a good melt strength. LDPE has however limited possibilities for downgauging, due to a low draw ratio, and a low stiffness.

[0003] Linear-low-density polyethylene (LLDPE) has greatly improved downgauging possibilities and excellent tear and impact properties; its stiffness however remains low and its processability is well below that of LDPE. Also, conventional LLDPE's optical properties do not match those of LDPE. Optical properties of LLDPE have been improved by using metallocene-catalysed LDPE (mLLDPE) resins; stiffness is however not improved in these products and the processability of these grades is generally worse than that of conventional LLDPE.

[0004] Wherever high rigidity is needed, LDPE and LLDPE compositions will require overly thick structures. Especially for LLDPE, where excellent impact and tear properties render its downgauging capability useful, the lack of rigidity may be a main drawback. High rigidity maybe a requirement for the end product, it is very often a necessity for product handling.

[0005] In the production of such polyethylene compositions, it is possible to use reaction systems based on a Ziegler-Natta catalyst or a chromium-based catalyst. These reaction systems require a high concentration of comonomer. This suffers from a drawback in that high concentration of comonomer results in increased solubility of the polyethylene produced in a slurry process. One consequence of the increased solubility of polymer is that there is a high incidence of reactor fouling. Use of a high concentration of comonomer is also costly because of the need to recycle unincorporated comonomer.

[0006] It is an aim of the present invention to overcome these disadvantages.

[0007] The present invention provides use of a metallocene catalyst component of general formula $R''(CpR_m)(Cp'R'_n)MQ_2$ in the production of linear low density polyolefin, wherein Cp is a cyclopentadienyl moiety, Cp' is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge imparting stereorigidity to the component; each R is independently hydrogen or hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq m \leq 4$; each R' is independently hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq n \leq 8$; M is a Group IVB transition metal or vanadium; and each Q is hydrocarbyl having 1 to 20 carbon atoms or halogen; the metallocene having a centroid-M-centroid angle in the range 105° to 125° .

[0008] Figure 1 shows the effect of decreasing the centroid-M-centroid angle in Zr-based metallocenes. The metallocenes of the present invention have a very open structure which permits the facile incorporation of comonomer with larger substituents such as hexene in polyolefin production. In this way, LLDPE with densities around 0.9 or lower may be produced at a commercially acceptable polymerisation temperature in a slurry process. The production of LLDPE with such low densities has hitherto not been possible with Cr-based and closed structure Cent-Zr-Cent ($>125^\circ$) metallocenes in a loop slurry process. Lower comonomer concentrations need be used in the process thereby reducing the likelihood of reactor fouling and avoiding excessive use of expensive comonomer.

[0009] Preferably Cp is a substituent cyclopentadienyl in which each R is independently XR^*3 in which X is C or Si and each R* is independently H or hydrocarbyl having 1 to 20 carbon atoms. More preferably the cyclopentadienyl is substituted with Ph_2CH , Me_3C , Me_3Si , Me, Me and Me_3C , Me and $SiMe_3$, Me and Ph, or Me and $CH_3-CH-CH_3$.

[0010] Preferably, each R' is independently YR'''_3 in which Y is C or Si and each R''' is independently H or hydrocarbyl having 1 to 20 carbon atoms.

[0011] The structural bridge R'' is generally alkylidene having 1 to 20 carbon atoms, a dialkyl germanium or silicon or siloxane, alkyl phosphine or amine, preferably Me-C-Me, Ph-C-Ph, $-CH_2-$, Et-C-Et, Me-Si-Me, Ph-Si-Ph or Et-Si-Et.


[0012] The metal M is preferably Zr or Hf and each Q is preferably Cl.

[0013] In order to maximise comonomer incorporation, it is preferred that the centroid-M-centroid angle is no more than 119° .


[0014] In a further aspect, the present invention provides a process for the preparation of a linear low-density polyolefin, which comprises reacting an olefin monomer with hydrogen and an α -olefin comonomer in the presence of a catalyst comprising (i) the metallocene catalyst and (ii) an aluminium- or boron-containing cocatalyst. The comonomer is preferably hexene, typically present in an amount of from 2 to 10, preferably 2 to 5% by weight of the total reaction mixture.

[0015] Suitable aluminium-containing cocatalysts comprise an alumoxane, an alkyl aluminium and/or a Lewis acid.

[0016] The alumoxanes usable in the process of the present invention are well known and preferably comprise oligomeric linear and/or cyclic alkyl alumoxanes represented by the formula:



10 for oligomeric, linear alumoxanes and



20 for oligomeric, cyclic alumoxane, wherein n is 1-40, preferably 10-20, m is 3-40, preferably 3-20 and R is a C₁-C₈ alkyl group and preferably methyl. Generally, in the preparation of alumoxanes from, for example, aluminium trimethyl and water, a mixture of linear and cyclic compounds is obtained.

[0017] Suitable boron-containing cocatalysts may comprise a triphenylcarbenium boronate such as tetrakis-pentafluorophenylborato-triphenylcarbenium as described in EP-A-0427696, or those of the general formula [L⁺-H]⁺ [B Ar₁ Ar₂ X₃ X₄]⁻ as described in EP-A-0277004 (page 6, line 30 to page 7, line 7).

[0018] The catalyst system may be employed in a solution polymerisation process, which is homogeneous, or a slurry process, which is heterogeneous. In a solution process, typical solvents include hydrocarbons with 4 to 7 carbon atoms such as heptane, toluene or cyclohexane. In a slurry process it is necessary to immobilise the catalyst system on an inert support, particularly a porous solid support such as talc, inorganic oxides and resinous support materials such as polyolefin. Preferably, the support material is an inorganic oxide in its finely divided form.

[0019] Suitable inorganic oxide materials which are desirably employed in accordance with this invention include Group 2a, 3a, 4a or 4b metal oxides such as silica, alumina and mixtures thereof. Other inorganic oxides that may be employed either alone or in combination with the silica, or alumina are magnesia, titania, zirconia, and the like. Other suitable support materials, however, can be employed, for example, finely divided functionalized polyolefins such as finely divided polyethylene.

[0020] Preferably, the support is a silica having a surface area comprised between 200 and 900 m²/g and a pore volume comprised between 0.5 and 4 ml/g.

[0021] The amount of alumoxane and metallocenes usefully employed in the preparation of the solid support catalyst can vary over a wide range. Preferably the aluminium to transition metal mole ratio is in the range between 1:1 and 100:1, preferably in the range 5:1 and 50:1.

[0022] The order of addition of the metallocenes and alumoxane to the support material can vary. In accordance with a preferred embodiment of the present invention alumoxane dissolved in a suitable inert hydrocarbon solvent is added to the support material slurried in the same or other suitable hydrocarbon liquid and thereafter a mixture of the metallocene catalyst component is added to the slurry.

[0023] Preferred solvents include mineral oils and the various hydrocarbons which are liquid at reaction temperature and which do not react with the individual ingredients. Illustrative examples of the useful solvents include the alkanes such as pentane, iso-pentane, hexane, heptane, octane and nonane; cycloalkanes such as cyclopentane and cyclohexane, and aromatics such as benzene, toluene, ethylbenzene and diethylbenzene.

[0024] Preferably the support material is slurried in toluene and the metallocene and alumoxane are dissolved in toluene prior to addition to the support material.

[0025] Where the reaction is performed in a slurry using, for example, isobutane, a reaction temperature in the range 70°C to 110°C may be used. Where the reaction is performed in solution, by selection of a suitable solvent a reaction temperature in the range 150°C to 300°C may be used. The reaction may also be performed in the gas phase using a suitably supported catalyst.

[0026] A linear low-density polyethylene is obtainable from the process with a density below 0.93g/cc and preferably in the range 0.90 to 0.92. The polyethylene preferably has a molecular weight distribution in the range 2 to 4.5, preferably around 3 and more preferably is partially long chain branched so as to facilitate processing.

[0027] This invention will now be described in further detail by way of example only, with reference to the following

Examples and accompanying drawings, in which:

[0028] FIGURE 1 shows centroid-M-centroid angles for some metallocenes.

Example 1

Catalyst Preparation

[0029] $\text{Me}_2\text{CCpFluZrCl}_2$ was prepared in accordance with the method of Razavi and Ferrara published in Journal of Organometallic Chemistry, 435 (1992) pages 299 to 310.

[0030] The support used is a silica having a total pore volume of 4.22 ml/g and a surface area of 322 m²/g. This silica is further prepared by drying in high vacuum on a schlenk line for three hours to remove the physically absorbed water. 5g of this silica are suspended in 50 ml of toluene and placed in a round bottom flask equipped with magnetic stirrer, nitrogen inlet and dropping funnel.

[0031] An amount of 0.31 g of the metallocene is reacted with 25 ml of methylalumoxane (MAO 30 wt% in toluene) at a temperature of 25°C during 10 minutes to give a solution mixture of the corresponding metallocenium cation and the anionic methylalumoxane oligomer.

[0032] Then the resulting solution comprising the metallocenium cation and the anionic methylalumoxane oligomer is added to the support under a nitrogen atmosphere via the dropping funnel which is replaced immediately after with a reflux condenser. The mixture is heated to 110°C for 90 minutes. Then the reaction mixture is cooled down to room temperature, filtered under nitrogen and washed with toluene.

[0033] The catalyst obtained is then washed with pentane and dried under a mild vacuum.

Examples 2 to 7

Bench Scale Polymerisation procedures and results

[0034] Each polymerisation run was performed as described in the following Tables in a 4l autoclave type reactor. In all cases a polymerisation temperature of 80°C was used and the diluent was 2l of isobutane. The catalyst in each case was prepared in accordance with the method indicated.

[0035] It will be apparent from each of Examples 2a, 2b, 2c and 3, as set out in Tables 1 to 4 respectively, that polyethylene products of low density are obtainable according to the invention, especially in the presence of hexene comonomer. High molecular weights are also apparent. This contrasts with comparative Examples 4 to 7 where higher densities are obtained.

Table 1 - Polymerization with Ph₂CpFluZrCl₂/SiO₂ ASAHI*, H1210.MAO* (Example 2a)

Influence of the hexene/ethylene wt ratio on the Fluff density

Entry	C6/C2 wt%	Hourly Prod. (gPE/gcat/h)	MI ₂ (g/10min)	HLM ₂ (g/10min)	SR	Density (g/cc)	Mn (kDa)	Mw (kDa)	Mz (kDa)	D	D'
1	0.00	820	0.06	2.09	37	0.942	43	201	650	4.7	3.2
2	0.41	1,620	too low	0.32	/	0.914	76	304	918	4.0	3.0
3	0.61	2,540	too low	0.17	/	0.918	76	336	958	4.4	2.9
4	0.81	2,130	too low	0.36	/	0.912	81	307	902	3.8	2.9
5(1)	1.22	700	0.06	2.74	44	0.908	35	197	677	5.7	3.4
6(2)	1.22	3854	too low	0.08	/	0.898	/	/	/	/	/
7(2)	1.62	12644	too low	0.12	/	0.896	/	/	/	/	/

Monomer: 6wt% ethylene; (1):4wt%ethylene

Hydrogen: 0.25 N1

Key: MI₂ = Melt index; Mn = number average molecular weight; Mw = weight average molecular weight; D = Mw/Mn; D' = Mz/Mw; SR = Shear Ratio (HLM₂/MI₂)

* made according to the method of Razavi and Atwood J. Organometallic Chem. 459 (1993), 117-123.

Table 2 - Polymerization with Ph₂CCpFluZrCl₂/SiO₂ ASAHI', H121c.MAO* (Example 2b)

Influence of the hexene/ethylene wt ratio on the fluff density

Entry	Ethylene (wt%)	Hydrogen (Nl)	1-hexene (wt%)	C6/C2 wt% ratio	Hourly Prod. (gPE/gCat/h)	MI ₂ (g/10min)	HlMI (g/10min)	SR	Density (g/cc)
1	6	0.25	2.44	0.41	1,560	11.29	too high	/	0.923
2	4	0.25	4.88	1.22	880	80.00	too high	/	0.918

* made according to the method of Razavi and Atwood J. Organometallic Chem. 452 (1993), 117-123

Table 3 - Polymerization with $\text{Ph}_3\text{CCpFluZrCl}_2/\text{SiO}_2$ ASAHI H121c.MAO* (Example 2c)

Influence of the hydrogen content on the melt index

Entry	Hydrogen	Hourly Prod.	MI ₂	HLM1	SR	Density	MN	MW	Mz	D	D'
		(gPE/gCat/h)	(g/10min)	(g/10min)		(g/cc)	(kDa)	(kDa)	(kDa)		
1	0.00	880	too low	too low	/	0.913	-	-	-	-	-
2	0.25	1,620	too low	0.32	/	0.914	76	304	918	4.0	3.0
3	1.00	1,200	0.27	9.91	36	0.918	39	131	444	3.4	3.4

C6/C2 wt ratio:0.41

Key: MI₂ = Melt index; Mn = number average molecular weight; Mw = weight average molecular weight;
D = Mw/Mn; D' = Mz/Mw; SR = Shear Ratio (HLM1/MI₂)
*made according to Razavi and Atwood J.Organometallic Chem. 497 (1995), 105-111

Table 4

Polymerization with Me ₂ C(3tBuCp)FluZrCl ₂ /SiO ₂ , ASAHI H121C.MAO* (Example 3)							
Entry	Ethylene (wt%)	hydrogen (NI)	C6/C2 wt% ratio	Hourly Prod. (gPE/gCat/h)	MI ₂ (g/10min)	HLMI (g/10min)	Density (g/cc)
1	6	0.25	0.00	900	too low	too low	0.930
2	6	0.25	0.41*	2,670	too low	0.06	0.917
3	6	0.25	0.41	3,280	too low	0.13	0.920
4	6	0.25	0.61*	2,600	too low	0.03	0.913
5	6	0.25	0.61	3,550	too low	0.01	0.913
6	6	0.25	0.81	2,770	too low	0.16	0.913
7	4	0.25	1.22*	1,550	too low	1.20	0.910
8	3	0.25	1.62*	1,410	too low	1.60	0.907

(*): no prepolymer.

* made according to Razavi and Atwood J.Organometallic Chem. 520 (1996), 115-120

Table 5 - Polymerization with Et(THI)₂ZrCl₂/SiO₂, MAO (Example 4 - Comparative)

Entry	Ethylene (Wt%)	Hydrogen (Nl)	1-hexene (wt%)	C6/C2 wt%	Hourly Prod. (gPE/gCat/h)	MI, (g/10min)	HLMI (g/10min)	SR	Density
				ratio					
1	6	0.25	0	0	9,175	too low	0.06	/	0.946
2	6	0.25	2.44	0.41	23,000	0.09	6.89	77	0.933
3	6	0.25	3.66	0.61	14,817	0.04	3.85	89	<0.930

Table 6 - Polymerization with Et(Ind)₂ZrCl₂/SiO₂, MAO (Example 5 - Comparative)

Entry	Ethylene (wt%)	Hydrogen (Nl)	1-hexene (wt%)	C6/C2 wt% ratio	Hourly Prod. (gPE/gCat/h)	MI ₂ (g/10min)	HLM1 (g/10min)	SR	Density (g/cc)
1	6	0.25	0.00	0.00	3,430	0.55	28.2	51	0.951
2	6	0.25	0.61	0.10	6,040	0.87	47.5	55	0.942
3	6	0.25	1.22	0.20	7,700	0.05	5.49	122	0.938
4	6	0.25	2.44	0.41	10,280	0.03	4.49	140	0.932
5	6	0.25	3.66	0.61	10,020	0.27	17.97	67	<0.930
6	6	0.25	4.88	0.81	5,600	1.54	73.93	48	<0.930

Table 7- Polymerization with (nBuCp)₂ZrCl₂/SiO₂. MAO (Example 6 - Comparative)

Entry	Ethylene (wt%)	Hydrogen (NI)	1-hexene (wt%)	C6/C2 wt% ratio	Hourly Prod. (gPE/gCat/h)	MI ₂ (g/10min)	HMI (g/10min)	SR	Density
1	6	0.25	0.00	0.00	4,506	0.58	11.43	20	0.956
2	6	0.25	0.30	0.05	4,400	1.66	28.08	17	0.947
3	6	0.25	1.22	0.20	6,480	1.89	30.60	16	0.944
4	6	0.25	2.44	0.41	7,050	2.05	32.54	16	0.936
5	6	0.25	3.66	0.61	6,800	2.36	37.97	16	0.933
6	6	0.25	4.88	0.81	6,720	2.67	44.72	17	0.930

Table 8 - Polymerization with (iBuCp)₂ZrCl₂/SiO₂. MAO (Example 7 - Comparative)

Entry	Ethylene (wt%)	Hydrogen (NI)	1-hexene (wt%)	C6/C2 wt% ratio	Hourly Prod. (gPE/gcat/h)	MI ₂ (g/10min)	HLMI (g/10min)	SR	Density
1	6	0.25	0.00	0.00	7,900	3.07	54.38	18	0.955
2	6	0.25	1.22	0.20	8,840	4.290	69.37	16	0.943
3	6	0.25	2.44	0.41	12,520	4.43	69.80	16	0.938
4	6	0.25	3.66	0.61	10,600	4.71	97.57	21	0.934
5	6	0.25	4.88	0.81	7,200	5.16	86.33	17	0.935

Examples 8 to 11

Pilot Plant Scale Polymerisation procedures and results

- 5 [0036] The supported metallocene catalyst of Example 2 was used on a pilot plant scale in the 70 litre loop reactor under the conditions set out in Table 9. Table 9 also shows the results of these pilot plant scale examples, which confirm the earlier bench scale results.

TABLE 9


Example	8	9	10	11
CATALYST TYPE	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp ZrCl ₂ /SiO ₂ .MAO
LOOP OPER. COND.				
Temp (°C)	85	85	85	80
Alkyl (TIBAL) (ppm/iC ₄)	250	250	250	250
Antifouling (ppm/iC ₄)	4	4	4	4
C ₂ - (kg/h)	7	8.5	7.5	7
C ₆ - (cc/h)	650	1049	1033	1467
H ₂ (NI/h)	5	5	5	5
iC ₄ (kg/h)	26	26	26	26
OFF-GAS FINAL				
2- (wt%)	5.6	6.7	6.0	6.4
C ₆ - (wt%)	0.88	1.38	1.23	2.07
H ₂ (mole%)	0.024	0.028	0.029	0.031
C ₆ -/C ₂ - ratio	0.16	0.21	0.21	0.32
H ₂ /C ₂ - ratio	0.004	0.004	0.005	0.005
CATALYST TYPE	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO	(Ph) ₂ C Cp Flu ZrCl ₂ /SiO ₂ .MAO
FLUFF FINAL				
HLMI (g/10')	0.66	0.53	0.97	1.24
MI ₂ (g/10')	****	****	****	****
MI ₅ (g/10')	****	****	****	****
SR2	****	****	****	****
Density (g/cc)	0.918	0.917	0.914	0.912
Bulk Density (g/cc)	0.37	0.37	0.37	0.37

Claims

1. Use of a metallocene catalyst component of general formula $R''(CpR_m)(Cp'R'_n)MQ_2$ in the production of linear low density polyolefin, wherein Cp is a cyclopentadienyl moiety, Cp' is a substituted or unsubstituted fluorenyl ring; R'' is a structural bridge imparting stereorigidity to the component; each R is independently hydrogen or hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq m \leq 4$; each R' is independently hydrocarbyl having 1 to 20 carbon atoms in which $0 \leq n \leq 8$; M is a Group IVB transition metal or vanadium; and each Q is hydrocarbyl having 1 to 20 carbon atoms or halogen; the metallocene having a centroid-M-centroid angle in the range 105° to 125°.

2. Use according to claim 1, wherein Cp is a substituted cyclopentadienyl in which each R is independently XR^*_3 in which X is C or Si and each R^* is independently H or hydrocarbyl having 1 to 20 carbon atoms.
3. Use according to claim 2, wherein the cyclopentadienyl is substituted with Ph_2CH , Me_3C , Me_3Si , Me, Me and Me_3C, Me and $SiMe_3$, Me and Ph, or Me and $CH_3-CH-CH_3$.
4. Use according to any one of claims 1 to 3, wherein each R' is independently YR'''_3 in which Y is C or Si and each R''' is independently H or hydrocarbyl having 1 to 20 carbon atoms.
5. Use according to any one of the preceding claims, wherein R'' is alkylidene having 1 to 20 carbon atoms, a dialkyl germanium or silicon or siloxane, alkyl phosphine or amine.
6. Use according to claim 5, wherein R'' is Me-C-Me, Ph-C-Ph, $-CH_2-$, Et-C-Et, Me-Si-Me, Ph-Si-Ph or Et-Si-Et.
7. Use according to any one of the preceding claims, wherein M is Zr or Hf.
8. Use according to any one of the preceding claims, wherein each Q is Cl.
9. Use according to any one of the preceding claims, wherein the centroid-M-centroid angle is no more than 119° .
10. Use according to any one of the preceding claims, wherein the polyolefin is a polyethylene.
11. A process for the preparation of a linear low-density polyolefin, which comprises reacting an olefin monomer with hydrogen and an α -olefin comonomer in the presence of a catalyst comprising (i) a metallocene catalyst component as defined in any one of claims 1 to 10 and (ii) an aluminium- or boron-containing cocatalyst.
12. A process according to claim 11, wherein the olefin monomer is ethylene and the polyolefin is polyethylene.
13. A process according to claim 12, wherein the comonomer comprises 1-hexene.
14. A process according to claim 13, wherein the 1-hexene is present in an amount of from 2 to 10, preferably 2 to 5 % by weight of the total reaction mixture.
15. A process according to any one of claims 11 to 15, wherein the cocatalyst comprises an alumoxane, an alkyl aluminium, a triphenylcarbenium boronate and/or a Lewis acid.
16. A process according to any one of claims 11 to 15, wherein the catalyst is supported on an inert support.
17. A process according to claim 16, wherein the inert support comprises a silica support.
18. A process according to claim 16 or claim 17, which is performed in a slurry..
19. A process according to claim 18, wherein the temperature is from $70^\circ C$ to $110^\circ C$.
20. A process according to any one of claims 11 to 15, which is performed in a solvent at a temperature in the range $150^\circ C$ to $300^\circ C$.
21. A process according to claim 20, wherein the solvent comprises isobutane.
22. A linear low-density polyethylene obtainable from a process according to any one of claims 11 to 18, the density of which is below 0.93 g/cc.
23. A linear low-density polyethylene according to claim 22, wherein the density is in the range 0.90 to 0.92.
24. A linear low-density polyethylene according to claim 22 or claim 23, which has a molecular weight distribution (D) in the range 2 to 4.5.
25. A linear low-density polyethylene according to any one of claims 22 to 24, which is partially long chain branched.

Figure 1





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 98 11 2233

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP 0 653 445 A (TOSOH CORP) 17 May 1995 * examples 1-3 * * page 2, line 3 - line 5 * * page 6, line 28 - line 33 *	1,5-13, 15,22-24	C08F4/62 C08F210/16
X	US 5 317 036 A (BRADY III ROBERT C ET AL) 31 May 1994 * column 20, line 24 - line 29 * * column 23; examples 1-25 * * column 26 - column 27; tables III,IV * * column 29; examples 26-28; table IX *	1,5-13, 15,22,23	
X	EP 0 786 466 A (TOSOH CORP) 30 July 1997 * example 14 * * page 12, line 57 - page 13, line 2 * * page 12, line 53 - line 54 *	1-3,5-13	
X	EP 0 668 295 A (UNION CARBIDE CHEM PLASTIC) 23 August 1995 * page 8, line 48 - page 10, line 16 * * page 11 - page 13; tables 1,2 * * page 7, line 10 - line 13 * * page 8, line 29 *	11-13, 15-19	TECHNICAL FIELDS SEARCHED (Int.Cl.6) C08F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 2 December 1998	Examiner Fischer, B
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04/C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 98 11 2233

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

02-12-1998

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0653445 A	17-05-1995	JP 7133323 A	23-05-1995
US 5317036 A	31-05-1994	AT 137509 T	15-05-1996
		AU 657076 B	23-02-1995
		AU 4902893 A	28-04-1994
		BR 9304244 A	05-07-1994
		CA 2108528 A,C	17-04-1994
		CN 1088939 A	06-07-1994
		CZ 9302179 A	18-05-1994
		DE 69302458 D	05-06-1996
		DE 69302458 T	14-11-1996
		DK 593083 T	10-06-1996
		EP 0593083 A	20-04-1994
		ES 2089673 T	01-10-1996
		FI 934579 A	17-04-1994
		GR 3019818 T	31-08-1996
		HU 66408 A	28-11-1994
		JP 2762025 B	04-06-1998
		JP 6192311 A	12-07-1994
		NO 933720 A	18-04-1994
		NZ 248961 A	26-10-1994
		PL 173786 B	30-04-1998
		SK 113293 A	11-05-1994
		ZA 9307676 A	05-05-1994
EP 0786466 A	30-07-1997	JP 10226694 A	25-08-1998
EP 0668295 A	23-08-1995	AT 166887 T	15-06-1998
		AU 689178 B	26-03-1998
		AU 1227895 A	24-08-1995
		AU 6808098 A	16-07-1998
		AU 6808198 A	30-07-1998
		BR 9500663 A	31-10-1995
		CA 2142669 A	18-08-1995
		DE 69502744 D	09-07-1998
		DE 69502744 T	01-10-1998
		ES 2117829 T	16-08-1998
		JP 7258324 A	09-10-1995
		US 5672669 A	30-09-1997
		US 5674795 A	07-10-1997
		US 5648310 A	15-07-1997

EPO FORM P0439

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

THIS PAGE BLANK (USPTO)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE RI ANK (ISPTO)